



Durosil Products Limited

## PHYSICAL DATA

	DUROSIL DR11	DUROSIL DR6
Bulk Density (N/mm <sup>3</sup> )	2200 average 2000 minimum	2040 average 1950 minimum
Cold Crushing Strength (N/mm <sup>2</sup> )	31.0 average 20.0 minimum	20 average 17 minimum
Modulus of Rupture (48 hours)	8N	5N
Modulus Of Elasticity (48 hours)	361N	No data
Temperature Limitation	700°C	700°C
Drying Shrinkage (BS812:Pt 120)	0.048-0.054	No data
Setting Time @ 20°C	Initial Set 2.5 hours Final Set 5 hours	No data
Pull-off Test (BS1881 Pt 207)	12.39N/mm <sup>2</sup>	No data